



# Curaçao

Collection Inside out 340

Technical data sheet

| <b>GENERAL</b>  |                         |                      |
|---|-------------------------|----------------------|
| Composition   |                         | 63%PP + 37%PL        |
| Roll width  |                         | 140cm                |
| Roll length   |                         | +/- 30m              |
| Weight  |                         | 650g/m               |
| <b>TESTS</b>  | <b>METHOD</b>           | <b>RESULT / U.M.</b> |
| Martindale  | UNI EN ISO 12947-2      | 50.000 cycles        |
| Pilling   | UNI EN ISO 12945-2      | 5                    |
| Colour fastness to light  | UNI EN ISO 105 B02      | 7                    |
| Fastness to rubbing (dry)   | UNI EN ISO 105 X12      | 4-5                  |
| Fastness to rubbing (wet)   | UNI EN ISO 105 X12      | 4-5                  |
| Colour fastness to (sea)water, chlorinated water  | UNI EN ISO 105 E02-E03  | 5                    |
| Seam slippage   | UNI EN ISO 13936-2 (mm) | 1.0 warp / 1.5 weft  |
| Burning behaviour   | FR EN 1021 part 1       | pass                 |
| <b>CERTIFICATS</b>  |                         |                      |
|  <p>FR EN 1021 PART 2 OPTIONAL (with FR foam)</p> |                         |                      |
| <b>CLEANING INSTRUCTIONS : EASY CLEAN</b>   |                         |                      |
|  <p>EASY CLEAN</p>                                |                         |                      |



**REMARKS**

\*\*\*INTENSIVE DOMESTIC AND CONTRACT USE\*\*\*

Slight color differences between production batches can occur.

The test results only apply to the samples tested.

Buvetex can't be kept liable for inappropriate use of the fabric.

