



Dott

Collection Berlage 347

Technical data sheet

GENERAL		
Composition		72% recycled PL + 28%PL
Roll width		140cm
Roll length		- / + 40m
Weight		848 gr/m
TESTS	METHOD	RESULT / U.M.
Martindale abrasion	UNI EN ISO 12947-2	25.000
Pilling (2.000 cycles)	UNI EN ISO 12945-2	5
Colourfastness to light	UNI EN ISO 105 B02	5
Fastness to rubbing (dry)	UNI EN ISO 105 X12	3-4
Fastness to rubbing (wet)	UNI EN ISO 105 X12	3
Seam slippage	UNI EN ISO 13936-2 (mm)	2.0 warp / 4.0 weft
Tensile strength	UNI EN ISO 13934-1 (N)	>350
Tear strength	UNI EN ISO 13937-3 (N)	>20
Burning behaviour	BS 5852 source 0+1	pass
CERTIFICATS		
 FIRE RETARDANT		
 RECYCLED CONTENT		

CLEANING INSTRUCTIONS



EASY CARE



REMARKS

INTENSIVE CONTRACT AND DOMESTIC USE

Slight color differences between production batches can occur.

The test results only apply to the samples tested.

Buvetex can't be kept liable for inappropriate use of the fabric.