

# Jarama

Property	Test procedures	Compliance Requirement
Colour fastness to light Atlas CI 3000+, filter system H 80 hours, 1,2 W/m <sup>2</sup> 420nm T° black panel 100°C Um 20%	ISO 105 B06	>= 5 Blue scale
Tensile Strength	ISO 3376	>= 10 – N/mm <sup>2</sup>
Elongation at break	ISO 3376	40 – 70%
Tear growth – Bauman Method	ISO 3377-2	>= 40 - N
Flex endurance	ISO 5402	> 50.000 cycle
Adhesion of Finish	ISO 11644	>= 3 N/Cm
Crock meter test Dry 10 cycle Wet 10 cycle	ISO 105 X12	>= 4 Grey scale
Resistance to rubbing Dry 2.000 cycle Wet 300 cycle	ISO 11640	>= 4 Grey scale
Determination of burning behaviour	ISO 3795	OK mm/mm