

Valtellina

ORIGIN	European
AVERAGE SIZE	Average MQ 4,6
THICKNESS OF THE SKINS	Average 1.4-1.6 mm
KIND OF LEATHER	nappa
CLASS	full grain
TANNING	Chrome
GRANA	natural grain
FINISHING	water base - semi aniline

Property	Test procedures		Compliance Requirement	
Flexing endurance	ISO 5402		> 50.000 cycle	
Colour fastness to light	ISO 105 B02		>= 4 Blue scale	
Colour fastness to and for rubbing Sweat Alkaline Solution – ISO 11641 pH 8 Evaluation ISO 105 A03	ISO 11640	Dry	Cycle 500	Value >= 4
		Wet	80	= 3
		Sweat	50	= 3
Tear Strength single edge tear	ISO 3377-1		= 20	N
Finish Adhesion	ISO 11644		= 2,0	N/Cm
Determination of pH Difference figure (only for pH < 4)	ISO 4045		= 3,5 <= 0,7	
Average size	Average MQ 4,4 - 4,8			
Thickness of the skins	Average 1,6 – 1,8			

De onregelmatige korrel toont dat het een natuurproduct van hoge kwaliteit betreft. Enkel een keuze van de kleur is mogelijk op basis van het staalboek. Na versnijding is er geen terugname mogelijk.

Le grain irrégulier montre qu'il s'agit d'un produit de haute qualité. Le seul choix est celui de la couleur sur base de la collection. Après coupage, il n'y a pas de possibilité de reprendre la marchandise

The irregular grain shows it concerns a high quality product. The samples can only be used for colour reference. After cutting the hides it is not possible to return the goods.

Die unregelmässige Struktur zeigt dass es ein hochwertiges Naturprodukt ist. Es ist nur möglich Farbe auszuwählen auf grund des Musterbuch. Abschnitte werden nicht zurückgenommen.