

# Antico

<b>LEATHER QUALITY</b>	Cow Leather
<b>ORIGIN</b>	European
<b>AVERAGE SIZE</b>	Average 4,6 m2
<b>THICKNESS</b>	Average 0.8-1.0 mm
<b>CLASS</b>	half grain
<b>TANNING</b>	Chrome
<b>DRYING</b>	toggling
<b>GRANA</b>	flat natural grain
<b>FINISHING</b>	water based finishing
<b>COLOR</b>	strong kela two tone

Property	Test procedures		Compliance Requirement	
Flexing endurance	ISO 5402		> 50.000 cycle	
Colour fastness to light	ISO 105 B02		>= 3 Blue scale	
Colour fastness to and for rubbing Sweat Alcaline Solution – ISO 11641 pH 8 Evaluation ISO 105 A03	ISO 11640	Dry	Cycle	Value
		Wet	50	>= 3
		Sweat	20	>= 3
	20		20	>= 3
Tear Strength single edge tear	ISO 3377-1		>= 20	N
Finish Adhesion	ISO 11644		>= 2,0	N/Cm
Determination of pH Difference figure (only for pH < 4)	ISO 4045		>= 3,5 <= 0,7	
Average size	Average MQ 4,4 - 4,8			
Thickness of the skins	Average 0,8 – 1,0			