

# Nairobi

Property	Test procedures		Compliance Requirement	
Flexing endurance	ISO 5402		> 50.000 cycle	
Colour fastness to light	ISO 105 B02		≥ 5 Blue scale	
Colour fastness to and for rubbing Sweat Alkaline Solution – ISO 11641 pH 8 Evaluation ISO 105 A03	ISO 11640	Dry	Cycle 500	Value = 4
		Wet	80	= 4
		Sweat	50	= 4
Tear Strength single edge tear	ISO 3377-1		≥ 20	N
Finish Adhesion	ISO 11644		≥ 2,5	N/Cm
Determination of pH Difference figure (only for pH < 4)	ISO 4045		≥ 3,5 ≤ 0,7	
Average size	Average MQ 4,4 - 4,8			
Thickness of the skins	Average 0,8 – 1,0			