

Nuvola

Property	Test procedures	Compliance Requirement	Values obtained
Resistance to dry friction	iuf 450, bs 1006, din 53329	1000 cycles	leather = 5 buffer = 5
Resistance to damp friction	iuf 450, bs 1006, din 53329	200 cycles	leather ≥ 4 tampone ≥ 4
Resistance to artificial sweat	iuf 450, bs 1006, din 53329	120 cycles	leather ≥ 4 tampone ≥ 4
Locking	iuf 470	N/cm	≥ 3
Cracking fatigue	iup 20, uni 8433, din 53351	50.000 cycles	no cracking
Solidity in light	iuf 402 xenotest, bs 1006-b02, din 54004	scale of blues	≥ 4
Aging from heat	din 54004	scale of greys	≥ 4
Colour control	bs 950 part 1	artificial daylight d65	-