



Alexia

Artificial leather collection

Technical data sheet

GENERAL		
Composition surface / back cloth		50%PL + 50%PU
Roll width		140cm
Roll length		+/- 25m
Weight		520gr/m ²
Thickness		1.0-1.1mm
TESTS	METHOD	RESULT / U.M.
Colour fastness to light	UNI EN ISO 105 B02	6-7
Flexing endurance Bally Flex	UNI 4818-13 + PDP 171	no damage
Hidrolysis resistance (>100.000 cycles, > 5 years)	UNI 4818-29 / 4818-13	no damage
Martindale abrasion	UNI EN ISO 12947-2	100.000 cycles
Colour fastness to (sea)water, swimming pool water	UNI EN ISO 105 E01, B04, E04 E05, E06	5
Burning behaviour	FR EN 1021 part 1+2 FR BS 5852 source 0+1	pass
CERTIFICATS		
 <p>FIRE RETARDANT</p>		
Reach compliant, solvent free, 100% health safety, 100% environment friendly		
CLEANING INSTRUCTIONS:		
 <p>EASY CLEAN, use a damp cloth.</p>		



Dijle 17/A
2800 Mechelen
TEL : 0032-15/40.90.60
www.buvetex.be

REMARKS

*** INTENSIVE CONTRACT AND DOMESTIC USE***

Slight color differences between production batches can occur.

The test results only apply to the samples tested.

Buvetex can't be kept liable for inappropriate use of the artificial leather.

