



# New Book

## Genuine leather collection

### Technical data sheet

<b>GENERAL</b>		
Composition		15%PL
Composition back cloth		85% leather
Weight		1.140gr/m <sup>2</sup>
<b>TESTS</b>	<b>METHOD</b>	<b>RESULT / U.M.</b>
Fastness to Crocking (dry)	UNI EN ISO 105 X12	>= 4
Colour fastness to light	UNI EN ISO 105 B02	>= 4
Pilling	UNI EN ISO 12945-2	>= 4-5
Martindale abrasion	UNI EN ISO 12947-2	>40.000 cycles
Burning behaviour	UNI EN ISO FR 1021 part 1+2	optional
<b>CERTIFICATS</b>		
 <p>FR 1021 PART 1+2 OPTIONAL</p>		
<b>CLEANING INSTRUCTIONS</b>		
 <p>EASY CLEAN</p>		
<b>REMARKS</b>		
<p><b>INTENSIVE USE FOR CONTRACT, DOMESTIC AND INDUSTRY</b></p> <p>Slight color differences between production batches can occur.</p> <p>The test results only apply to the samples tested.</p> <p>Buvetex can't be kept liable for inappropriate use of the genuine leather.</p>		