


Poncho

Genuine leather collection

Technical data sheet

GENERAL		
Thickness		1,2-1,4mm
Average surface		5,0sqm
Finishing		slightly corrected, semi-aniline
Tanning and effect		chrome tanned, 2-tone
TESTS	METHOD	RESULT / U.M.
Fastness to rubbing Veslic – dry (500 cycles)	UNI EN ISO 11640 / IUF 450	>= 4
Fastness to rubbing Veslic – wet (250 cycles)	UNI EN ISO 11640 / IUF 450	>= 4
Fastness to rubbing Veslic – sweat (80 cycles)	UNI EN ISO 11640 / IUF 450	>= 4
Colour fastness to light	UNI EN ISO 105 B02	4/5
Flexing endurance Bally Flex	UNI EN ISO 5402	>= 30.000 cycles
Tear strength (Bauman method)	UNI EN 3377-1	>= 20 N
Finish adhesion	UNI EN ISO 11644	>= 3,5 N/cm
Burning behaviour	UNI EN ISO FR 1021 part 1+2	pass
CERTIFICATS		
Ecologically safe production		
Compliant to the requirements of REACH, ILO, PCP, DMF, AZO dyestuffs		
		
FIRE RETARDANT		
CLEANING INSTRUCTIONS		
Slightly damp cloth		



Dijle 17/A
2800 Mechelen
TEL : 0032-15/40.90.60
www.buvetex.be

REMARKS

*****INTENSIVE DOMESTIC AND CONTRACT USE*****

Slight color differences between production batches can occur.

The test results only apply to the samples tested.

Buvetex can't be kept liable for inappropriate use of the genuine leather.