







# Bonaire

## Collection Inside Out 340

**Technical data sheet**

<b>GENERAL</b>		
Composition		66%AC + 34%PL
Roll width		140cm
Roll length		+/-30m
Weight		739gr/m
<b>TESTS</b>	<b>METHOD</b>	<b>RESULT / U.M.</b>
Martindale abrasion	UNI EN ISO 12947-2	60.000 cycles
Pilling	UNI EN ISO 12945-2	3-4
Colour fastness to light	UNI EN ISO 105 B02	>7
Fastness to rubbing	UNI EN ISO 105 X12	>3-4 (dry) / >3 (wet)
Colour fastness to water	UNI EN ISO 105 E01	>3-4 (stain) / >3 (col)
Tensile strength	UNI EN ISO 13934-1 (N)	>350
Tear strength	UNI EN ISO 13937-3 (N)	>20
Seam slippage	UNI EN ISO 13936-2 (mm)	4.0 warp / 2.0 weft
Burning behaviour	UNI EN ISO 1021 part 1	pass
<b>CERTIFICATS</b>		
Resistant to chlorine		
Mould resistant		
Does not absorb water		
<b>CLEANING INSTRUCTIONS</b>		
 <p>EASY CARE, using water and dish wash soap</p>     		



Dijle 17/A  
2800 Mechelen  
TEL : 0032-15/40.90.60  
[www.buvetex.be](http://www.buvetex.be)

**REMARKS**

\*\*\*INTENSIVE DOMESTIC AND CONTRACT USE\*\*\*

Slight color differences between production batches can occur.

The test results only apply to the samples tested.

Buvetex can't be kept liable for inappropriate use the fabric.

